SAHARA BUSINESS GROUP

BITUMEN 85-25

Characteristic	Value	Test Method
Specific Gravity @ 25/25°C	1.05 approx.	ASTM D-70
Penetration @ 25°C (dmm)	20-30	ASTM D-5
Softening Point (°C)	80-90	ASTM D-36
Ductility @ 25°C (cm)	3 min	ASTM D-113
Loss on Heating (%wt)	0.2 max	ASTM D-6
Flash Point (°C)	225 min	ASTM D-92
Solubility in CS_2 (%wt)	99 min	ASTM D-4

SAHARA BUSINESS GROUP